

Our Services



Design and Engineering



Production



Testing and Verification



Worldwide delivery,fast.






Corrosion Group

Scandinavias leading supplier of cathodic protection and corrosion prevention solutions.

Magneisum anode bag for underground tanks, steel structures and other applications.

Note: Magnesium anode bag contains anode and also a backfill mix of: Gypsum 75%, bentonite 20%, sodium sulphate 5%.



Note: Find price and shipping at the bottom page

You can provide complete cathodic protection to your underground installation by using the appropriate number of anodes. If done correctly, this will provide protection against corrosion for tanks, piping, sheet pilings, and other structures. This means that your underground object will not need to be replaced for many years due to corrosion.



Contact us at: <u>info@korrosionsgruppen.se</u> to get a quote or to place an order. You can also visit Anodefactory to place your order right away.

We offer anodes in all sizes, but with these sizes as standard.

| WEIGHT KG | WEIGHT TOTAL KG | CABLE | CABLE LENGHT | Ready to buy? |
|-----------|--------------------|---------------------------------|--------------|----------------------|
| 2 | 8 | INCL 10M, 10MM2 RED XLPE/PVC | 10 M | Request quote |
| 4 | 13 | INCL 10M, 10MM2 RED XLPE/PVC | 10 M | Buy now |
| 7,7 | 22 | INCL 10M, 10MM2 RED XLPE/PVC | 10 M | Buy now |
| 9 | 32 | INCL 10M, 10MM2 RED XLPE/PVC | 10 M | <u>Request quote</u> |
| 14,5 | 38,5 | INCL 10M, 10MM2 RED XLPE/PVC | 10 M | Buy now |

How to attache the anode cable: Cable lug, Pipe clamp, Pinbrazing







Pipe clamp



Pinbrazing




- 1. Decide size and quantity from the application chart.
- 2. Installing one anode: Place it near the center of the tank or the side.
- 3. Installing multiple anodes: Spread them evenly around the tank.
- 4. Remove shipping plastic packaging before installation.
- 5. Install anodes about two/three feet from the tank and at least as deep as the center line of the tank.

 Note: Anodes work best in locations with permanent moisture, so generally the deeper the better.

- 6.Place anode, stretch out the anode connection wire and extend over to a connection point on the tank fill pipe.
- 7. If necessary, cover the anode with about six inches of backfill and pour 5 gallons of water on the anode to saturate the prepared backfill. This in order to ensure a efficient current distribution.
- 8. Anode wire and the tank should be connected with a low-no electrical resistance. The connections should all be coated with moisture-proof material.

- 9. Ideally, the tank connection is made in the area of the tank fill pipe within the covered dome. With access to the anode wire, subsequent testing of the tank can include measurement of anode output and verification of performance.
- 10. Verify performance of the anode using an appropriate test procedure.





Material data sheet

| TYPE | TYPE MG | TYP MG S |
|-----------------|-----------|-----------|
| Aluminium | 5.5-6,5 | 0,4 |
| Copper | 0,02 Max | 0,3 |
| Silicon | 0,10 Max | 0,78 |
| Iron | 0,05 Max | 0,51 |
| Maganese | 0,15-0,50 | 1,5 |
| Zinc | 2,50-3,50 | 1,2 |
| Other (each) | 0,05 Max | 0,46 |
| Magnesium | Remaining | Remaining |
| Potential V | -1,5 | -1,7 |
| Capacity A*H/KG | 1230 | 1230 |



Pricing and shipping

| Product | Pcs price |
|---------------|-----------------|
| 2 KG | Request a quote |
| 4 KG | 294\$/pcs |
| 7,7 KG | 304\$/pcs |
| 9 KG | Request a quote |
| 14,5 KG | Request a quote |

We offer worldwide shipping between 1-3 weeks.

Shipping price depends on the weight of the order and therefore is included in your quote or order confirmation.

We also offer our customers bulk discounts:

| 2 pcs | -5 % |
|--------|------|
| 5 pcs | -10% |
| 20 pcs | -20% |
| 25 pcs | -25% |

